

DERAY®-KY 175

Semi-rigid thin wall Kynar®

Clear, thin wall Kynar® heat shrink tubing ideal for electronic, automotive and military applications requiring protection and see through inspection in aggressive environments.



Features and Benefits

- Highly flame retardant
- Semi-rigid
- High withstand to abrasion and cut-through
- Excellent chemical and solvent resistance
- Shrink ratio: 2:1
- Continuous operating temperature: -55°C to 175°C
- Shrink temperature: 175°C min.

- VW 60360-3
- CNES approved and listed in Matrex database
- ECSS-Q-ST-70-02

Typical Applications

- Strain relief and insulation of high temperature wires
- Excellently suitable for applications where high chemical and abrasion resistance is required
- All areas where outstanding electrical insulation is required

Standards

- UL 224 125C VW-1 - UL file # E107857
- CSA 22.2 No 198.1 125C - CSA file # 065789_0_000
- DEF STAN 59-97 Type 3
- BS G198 Part 4 Type 20
- VG 95343 Part 5 Type F
- QPL SAE AS23053/8
- PAN 6491

2:1

Shrink ratio

-55°C - 175°C (-67°F to 347°F)

Continuous operating temperature

Markets:

Automotive, Industrial, Aerospace, Defense, Mass Transit

Standards:



Kynar® is a registered trademark of ATOFINA

DERAY®-KY 175


ORDER NUMBER	EXPANDED	RECOVERED		DELIVERY UNITS	
	INTERNAL DIAMETER (MIN) D	INTERNAL DIAMETER (MAX) D	TOTAL WALL THICKNESS (NOM) W	SPOOL*	LENGTHS
	<i>mm (in)</i>	<i>mm (in)</i>	<i>mm (in)</i>	<i>m (ft)</i>	<i>1,22 m (48 in)</i>
0047	1.2 (3/64)	0.6 (0.024)	0.24 (0.009)	300 (984)	25
0063	1.6 (1/16)	0.8 (0.031)	0.24 (0.009)	300 (984)	25
0094	2.4 (3/32)	1.2 (0.047)	0.24 (0.009)	300 (984)	25
0125	3.2 (1/8)	1.6 (0.063)	0.24 (0.009)	300 (984)	25
0187	4.8 (3/16)	2.4 (0.094)	0.24 (0.009)	300 (984)	25
0250	6.4 (1/4)	3.2 (0.126)	0.30 (0.012)	300 (984)	10
0375	9.5 (3/8)	4.8 (0.189)	0.30 (0.012)	150 (492)	10
0500	12.7 (1/2)	6.4 (0.252)	0.30 (0.012)	100 (328)	10
0750	19.0 (3/4)	9.5 (0.374)	0.40 (0.016)	50 (164)	10
1000	25.4 (1)	12.7 (0.500)	0.50 (0.020)	50 (164)	10

Ordering

Select a dimension which will shrink snugly over the application to be covered. If recovery is restricted the resultant wall thickness will be less than specified.

- Select options:
 - Color: Clear (CL)
 - Approval: Standard, VG or QPL
- Please specify the product name, order number and options you require:
 - Example: DERAY®-KY 175, 0125 or 1/8 in, clear, VG

Please contact your Customer Service Representative for information on custom colors, sizes, lengths and material data sheet.



We advise that customers should separately evaluate the suitability of our products for their particular application. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. Please ask for the latest version of this data sheet. Subject to modification without prior notice.

For further information, please contact:

Americas: 800 422 6872
Canada: 800 845 6808

Asia Pacific: +86 512 82280099
Europe: +49 2226 9047 355

Technical data

PROPERTY	CURRENT VALUES	TEST METHODS
MATERIAL		
Material	PVDF, modified; free of lead and cadmium	n/a
Surface	smooth	n/a
Specific gravity	1.80 g/cm ³ max.	ASTM-D 792, A-I
Shrink ratio	2:1	n/a
Longitudinal shrinkage	-6% max.	ASTM-D 2671
MECHANICAL		
Tensile strength	37 MPa	ASTM-D 2671
Elongation	450%	ASTM-D 2671
Secant modulus	750 MPa max.	ASTM-D 882
THERMAL		
Tensile strength after thermal ageing (168 h at 200°C)	45 MPa	IEC 811-1-2
Elongation after thermal ageing (168 h at 200°C)	230%	IEC 811-1-2
Tensile strength after thermal shock (4 h at 250°C)	48 MPa	IEC 811-1-2
Elongation after thermal shock (4 h at 250°C)	300%	IEC 811-1-2
Cold bend test	does not break at -55°C	ASTM-D 2671 Meth. C
Flammability	selfextinguishing	UL 224 VW-1
Shrink temperature	175°C min.	n/a
Storage temperature	40°C max.	n/a
Continuous operating temperature	-55°C to 175°C	IEC 216
CHEMICAL		
Corrosive action	non-corrosive	ASTM-D 2671 Meth. A
Compatibility with copper	non-corrosive	ASTM-D 2671 Meth. B
Resistance against chemicals	very good	n/a
Water absorption	0.07% max.	VDE 0473
Resistance against fungus	does not promote fungus growth	ISO 846
ELECTRICAL		
Dielectric strength	31.5 kV/mm	VDE 0303 Part 2
Spec. volume resistivity	10 ¹³ Ω x cm	VDE 0303 Part 3

Kynar® is a registered trademark of ATOFINA.

We advise that customers should separately evaluate the suitability of our products for their particular application. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. Please ask for the latest version of this data sheet. Subject to modification without prior notice.

For further information, please contact:

Americas: 800 422 6872
Canada: 800 845 6808

Asia Pacific: +86 512 82280099
Europe: +49 2226 9047 355